

ASP100 POLYASPARTIC FLOOR COATING

Product Introduction

Two-component varnish cured by aspartate resin and aliphatic isocyanate.

Product Features

- High solids, non-toxic, eco-friendly
- Good compressive strength and impact resistance
- No yellowing, good wear resistance

Application

It is mainly designed to be used in occasions with high decorative requirements such as commercial imitation PVC floors and colored sand floors.

Physical Parameters

Part A	Part B
Appearance:Colorless transparent liquid	Appearance: All colors liquid
Viscosity 25℃: 400MPaS	Viscosity 25℃: 100MPaS
Specific gravity 25°C: 1.02	Specific gravity 25°C: 1.01
Solids: 90%	Solids: 64%

Physical Properties After Curing	
Paint appearance	normal
7 days hardness	shore D 68
Abrasion (CS17 wheel 750g, 500 rpm)	25mg
Elongation at break (%)	15
Tensile strength (MPa)	23
Concrete adhesion (Mpa)	2.2
Impact resistance (1000g, 1m)	Pass

Construction Parameters

Blend ratio Roll coating: A: B = 1:1 mass ratio

Application time:

Temperature（℃）	10	20	30
Pot life (mins)	40	35	25

Construction conditions

Ambient temperature: 0℃-35 ℃, **Ambient humidity:** ≤85%

Substrate temperature: must be greater than the air dew point temperature 3 ℃ or more.

PERFLEX NOVEL MATERIALS
Distributed in Australia by Synergy Building Supplies.
236 Planet Street, Welshpool WA 6106, Australia
1300 655 853, sales@oxide.com.au

POLYASPARTIC COATING PIONEER



Cleaning agent: polyaspartic polyurea standard thinner

Drying time and painting interval

Temperature(℃)	20
Surface Dry(hrs)	3
Tack Free (hrs)	4
Recoat time	4

The above data is for guidance only. The actual drying time/interval time before coating can be longer or shorter depending on the film thickness of the coating, ventilation condition, temperature and humidity, etc.

Surface Treatment

- Rinse off salt and other water-soluble dirt with water
- Remove grease and oil with appropriate cleaners and degrease
- Concrete substrate must be ground and cleaned thoroughly
- Pay attention to the coating interval with the primer during construction

Storage Condition

Storage time: Part A: 12 months Part B: 12 months
Storage temperature: 5℃-35℃

Packaging Specification

Part A: 20KG Part B: 10KG

Security Measures

- Avoid contact with skin and eyes.
- If the paint comes in contact with the skin, it should be cleaned with an appropriate cleaning agent. If paint comes into contact with eyes, use plenty of water to flush and seek immediate medical attention.
- Ensure good ventilation.
- The paint contains combustible substances. Please keep away from sparks and do not smoke in the adjacent work area.
- Comply with all health and safety regulations on site.

Statement

The information provided in this product specification is based solely on our knowledge gained in the laboratory and in practice. However, since use of the product is usually beyond our control, so we only give a guarantee of the quality of the product itself. We reserve the right to amend the specification by prior notice.

PERFLEX NOVEL MATERIALS
Distributed in Australia by Synergy Building Supplies.
236 Planet Street, Welshpool WA 6106, Australia
1300 655 853, sales@oxide.com.au

POLYASPARTIC COATING PIONEER